

SECTION 08 88 60, X-RAY LEAD GLASS

PART 1 - GENERAL

1.01 SUMMARY

- A. X-Ray Lead Glass must be manufactured to glazing industry standards and provide the same shielding equivalent as the partition, wall or door wherein the X-Ray Glazing occurs.
- B. X-Ray Lead Glass must comply with the National Council on Radiation Protection and Measurements (NCRP) Report No. 147 "Structural Shielding Design for Medical X-Ray Imaging Facilities".
- C. Lead Equivalent shielding value as specified by the projects qualified health or medical physicist of record, familiar with the particular facility, room usage, equipment, and compliance with local and national Radiation Safety Standards.

1.02 REFERENCES

- A. Standards:** Comply with requirements of the National Council on Radiation Protection and Measurements (NCRP), Report No. 147 "Structural Shielding Design or Medical X-Ray Imaging Facilities".
- B. Comply with lead shielding equivalents** as specified by the qualified health radiation physicist report for this particular project.
 - DD-G-451**, Federal Specification, clear sheet / plate glass quality.
 - ASTM C 1036**, American Society for Testing and Materials, flat glass.
 - ANSI Z97.1**, American National Standards Institute "Safety Glazing Materials used in Buildings" and "Safety Performance Specifications and Methods of Test".
 - CPSA 16 CFR 1201, CAT II**, Consumer Product Safety Council "Safety Standard for Architectural Glazing Materials"

1.03 RELATED DOCUMENTS

- A. Related Specification Sections:** 13 49 00 X-Ray Protection, 08 34 40 Radiation Protective Doors, 09 29 60 Lead Lined Gypsum Board.

1.04 SUBMITTALS

- A. Technical Data:** Sizes, locations and verification of shielding equivalent protection value in compliance with this specification, project plans and radiation physicist shielding report.
- B. Product Data:** Submit manufacturers printed data and specifications for X-Ray Lead Glass including installation and maintenance instructions to ensure compliance with this specification, project plans and radiation physicist shielding report.
- C. Certificate of Compliance:** Manufacturer shall provide certificate of compliance indicating that X-Ray Lead Glass provided for this project has been produced in accordance with requirements specified herein and the radiation physicist shielding report.

1.05 DELIVERY, STORAGE AND HANDLING

- A. Product Handling:** Follow Manufacturer / Fabricator specific handling and storage requirements to prevent damage, scratches or breakage of fragile X-Ray Lead Glass. NEVER store outdoors, set flat or use knives or strong cleaners on X-Ray Lead Glass.

PART 2 - PRODUCTS

2.01 APPROVED MANUFACTURERS / SUPPLIERS

A. Liberty Shielding • www.libertyshielding.com • e-mail sales@libertyshielding.com • Phone: (423) 449-XRAY(9729), a recognized manufacturer / fabricator regularly engaged in the successful production of the products specified herein.

B. Lead Glass Pro • www.leadglasspro.com • e-mail: sales@leadglasspro.com, a recognized manufacturer / fabricator regularly engaged in the successful production of the products specified herein.

2.02 MATERIALS AND FABRICATION

X-Ray Lead Glass is an annealed, high density flat glass manufactured to glazing industry standards and provide the same shielding equivalent as the partition, wall or door wherein the X-Ray Glazing occurs. Each piece must be clearly labeled or identified as "X-Ray Lead Glass" and protective lead shielding thickness equivalency.

A. Thickness: 5/16" minimum in single layer or multiple layers as needed to obtain required shielding equivalent to meet lead thickness value in wall or partition that X-Ray Lead Glass occurs in.

B. Appearance: Clear with yellow hue due to radiation protective oxide and heavy metal contents. X-Ray Safety Glass, required at glazing locations in lead lined door vision lites or in side lites, borrowed lites or windows in wall locations within 24" of door openings, must be permanently labeled as impact resistant in compliance with ANSI Z97.1 and CPSC 16 CFR Part 1201 for impact resistance, as manufactured by Liberty Shielding • phone: (423) 449-XRAY (9729) • email: sales@libertyshielding.com • www.libertyshielding.com

C. Sizes: Single pane sizes up to and including 96" X 48" maximum, X-Ray Lead Glass must have a minimum density to provide proper shielding with no less than 60% total heavy metal oxide content and a minimum of 55% lead oxide content by weight.

PART 3 - EXECUTION

3.01 INSTALLATION

A. X-Ray Lead Glass must be carefully installed vertically into the lead lined frame per manufacturer's instructions. Window frame must be clean, square and plumb with 1/8" maximum space for clearance around the perimeter and allowance for appropriate seals, glazing tape or gaskets. Stops must be set snug but not too tight. Avoid pinching or unequal pressure points against X-Ray Lead Glass surfaces and edges.

B. Glass must be immediately cleaned and protected from damage by other trades or activities until the room is complete.

3.02 CERTIFICATION

A. Upon completion of X-Ray Lead Glass installation, Manufacturer / Fabricator shall furnish a certificate of compliance stating that all glazing materials are in accordance with this specification, the plans and the physicist shielding report for this project.

3.03 TESTING

A. After the X-Ray equipment has been installed and placed in operating condition but prior to occupancy and use, the radiation shielding shall be tested by the original calculating project health radiation physicist of record at Owner's expense.

END OF SECTION 08 88 60 X-RAY LEAD GLASS